

04/03/01 17:37:18

012.421.3685->

903 842 2190

Page 001

RECEIVED
4-3-01

The
Matrixx
Group

PRODUCT DATA SHEET - FPP3A15CC

PROPERTY	AVERAGE VALUE	TEST METHOD
MELT FLOW, g/10 min (230°C/2.16kg)	3	ASTM-D1238
FILLER CONTENT, %	15	Matrixx Method
SPECIFIC GRAVITY	1.00	ASTM-D792
NOTCHED IZOD IMPACT, ft-lbrin	2.0	ASTM-D256
GARDNER IMPACT, in-lb	< 10	ASTM-D5420
TENSILE YIELD STRENGTH, psi	7900	ASTM-D638
TENSILE ELONGATION @ YIELD, %	8	ASTM-D638
FLEXURAL MODULUS (tangent), psi	380,000	ASTM-D790
HDT @ 66 PSI, °F	N/A	ASTM-D648
HDT @ 264 PSI, °F	N/A	ASTM-D648
LINEAR MOLD SHRINKAGE, in/in	0.002 - 0.005	Matrixx Method
FLAMMABILITY, 1/8" & 1/16"	HB*	UL-94

* Internal Matrixx testing only; not currently approved by Underwriters Laboratories

This information is the best of our knowledge and belief, accurate and reliable. Because conditions of use are beyond our control, we make no warranty, expressed or implied, and specifically exclude any and all warranties of merchantability and fitness for any particular purpose. This material is sold "as is" without any other warranties. Our customers will conduct their own tests to determine the suitability of the material for their particular use. Notices herein shall be construed as permission or recommendation to practice a process or method without liability. The sole liability of The Matrixx Group for any claims arising out of the manufacture, use, or sale of its products shall be for the customer's purchase price or material replacement.

3/20-4/1/01